

Central Lancashire Online Knowledge (CLOK)

Title	Ferrocene-Based Nonphosphorus Copolymer: Synthesis, High-Charring Mechanism, and Its Application in Fire Retardant Epoxy Resin
Type	Article
URL	https://clock.uclan.ac.uk/id/eprint/20506/
DOI	https://doi.org/10.1021/acs.iecr.7b02980
Date	2017
Citation	Liao, Dui-Jun, Xu, Qi-Kui, McCabe, Richard W., Babu, Heeralal Vignesh, Hu, Xiao-Ping, Pan, Ning, Wang, De-Yi and Hull, T Richard (2017) Ferrocene-Based Nonphosphorus Copolymer: Synthesis, High-Charring Mechanism, and Its Application in Fire Retardant Epoxy Resin. Industrial & Engineering Chemistry Research, 56 (44). pp. 12639-12643. ISSN 1520-5045
Creators	Liao, Dui-Jun, Xu, Qi-Kui, McCabe, Richard W., Babu, Heeralal Vignesh, Hu, Xiao-Ping, Pan, Ning, Wang, De-Yi and Hull, T Richard

It is advisable to refer to the publisher's version if you intend to cite from the work.
<https://doi.org/10.1021/acs.iecr.7b02980>

For information about Research at UCLan please go to <http://www.uclan.ac.uk/research/>

All outputs in CLOK are protected by Intellectual Property Rights law, including Copyright law. Copyright, IPR and Moral Rights for the works on this site are retained by the individual authors and/or other copyright owners. Terms and conditions for use of this material are defined in the <http://clock.uclan.ac.uk/policies/>

Ferrocene-Based Non-phosphorus Copolymer: Synthesis, High-charring Mechanism and Its Application in fire retardant Epoxy Resin

Dui-Jun Liao[†], Qi-Kui Xu[†], Richard W. McCabe[‡], Heeralal Vignesh Babu[¶], Xiao-Ping Hu^{†‡}, Ning Pan[§], De-Yi Wang[¶], T. Richard Hull^{‡*}*

[†]School of materials Science and Engineering, Southwest University of Science and Technology, Mianyang 621010, P.R. China

[‡]Centre for Fire and Hazards Science, University of Central Lancashire, Preston PR1 2HE, UK.

[¶]IMDEA Materials Institute, C/Eric Kandel, 2, 28906 Getafe, Madrid, Spain

[§]Fundamental Science on Nuclear Wastes and Environmental Safety Laboratory, Southwest University of Science and Technology, Mianyang 621010, P. R. China

* Corresponding authors: Prof. Xiao Ping Hu; Prof. T. Richard Hull

E-mail addresses: huxiaoping@swut.edu.cn (Xiao Ping Hu); trhull@uclan.ac.uk

Additional Supporting Data

Table caption

Table S1. Chemical structures of pyrolysis compounds for PDPFDE at 700 °C under N₂

Figure captions

Figure S1. FTIR spectrum of DAF

Figure S2. ¹H NMR spectrum of DAF.

Figure S3. ¹³C NMR spectrum of DAF.






Figure S4. ¹H NMR spectrum of DCF.












Figure S5. GPC curve of PDPFDE.

Figure S6. DSC curve of PDPFDE in N₂ atmosphere.

Figure S7. The SEM image of the char residue of PDPFDE under nitrogen at 700 °C in muffle furnace for 30 min.

Table S1. Chemical structures of pyrolysis compounds for PDPFDE at 700 °C under N₂

Peak	t _R (min)	Name of compounds	molecular formula	M.W (g/mol)
1	1.52	carbon dioxide	CO ₂	44
2	1.89	cyclopentadiene		66
3	2.51	1-methyl-cyclopentadiene		80
4	2.74	benzene		78
5	4.46	toluene		92
6	5.41	2-ethylacridine		207
7	6.32	ethylbenzene		106
8	6.94	benzenemethanimine		105
9	8.47	1-actylcyclopentadiene		108
10	9.48	indane		118
11	9.79	indene		116
12	11.68	1-methylindene		130
13	12.11	naphthalene		128
14	13.66	2,6-dimethylnaphthalene		156
15	14.07	ferrocene		186
16	14.89	biphenyl		154

17	15.17	diphenylmethane		168
18	15.30	1-naphthalene-carbonitrile		153
19	16.66	bibenzyl		182
20	17.49	1H-phenalene		166
21	18.72	1-acetyl ferrocene		228
22	18.90	(E)-stilbene		180
23	19.28	1,4-dimethyl-7-(1-methylethyl) azulene		198
24	20.03	1,1',1''-(1-ethanyl-2-ylidene) tris-benzene		258
25	20.60	2,2'-diphenylethylamne		196
26	22.09	1,1'-diacetyl-ferrocene		270
27	22.39	Iron		56
28	23.99	3-methyl terphenyl		244




Figure S1. FTIR spectrum of DAF




Figure S2. ¹H NMR spectrum of DAF




Figure S3. ¹³C NMR spectrum of DAF




Figure S4. ^1H NMR spectrum of DCF




Figure S5. GPC curve of PDPFDE.




Figure S6. DSC curve of PDPFDE in N_2 atmosphere.




Figure S7. The SEM image of the char residue of PDPFDE under nitrogen at 700°C in muffle furnace for 30 min.

The Figure S7 represents the SEM image of the char residue of PDPFDE under nitrogen at 700°C in muffle furnace for 30 min. Based on the SEM image, we can clearly see the many nanowires existing in the char residue. However, the investigation of the detailed component and structure of the nanowires needs further study in the future.